



Product data sheet

Triflex Stone Design S

Use

Aggregate used with Triflex Stone Design R 1K to create the surface variant Triflex Stone Design.

Components

Component	Product
Aggregate	Triflex Stone Design S

Packaging

Component	Pack size
Aggregate	Bag: 25.00Kg

Stone options

Italian marble (1-4mm)

- Giallo Sienna
- Breccia Pernice
- Rosso Verona
- Marrone
- Bardiglio
- Ice Blue

Application conditions

Refer to Triflex Stone Design R 1K Product Data Sheet.

Substrate assessment / pretreatment / preparation

Ensure that the substrate is clean, dry and free from dust, laitance, grease, oil and any other contaminants and assess / pre-treat / prepare substrate in accordance with Triflex Project Specification proposal. The substrate must have a minimum fall of 2% or 1:50.

Mixing instructions

1. Thoroughly mix one bag of Triflex Stone Design R 1K with one bag of Triflex Stone Design S until it achieves a uniform consistency;
2. Use double agitator, concrete mixer or a compulsory mixer for at least 3 minutes.

The Triflex Stone Design S aggregate is added slowly and mixed into the resin. All the aggregate must be completely encased by the resin.

Mixing ratio

Triflex Stone Design R 1K 1.3Kg : 25Kg Triflex Stone Design S.

Application method

Trowel. For smoothing wet trowel lightly with soapy water.

Mixing ratio

Triflex Stone Design R 1K 1.3Kg : 25Kg Triflex Stone Design S.



Consumption

Surface layer thickness 8mm

Triflex Stone Design R 1K: 0.80Kg/m²

Triflex Stone Design S: 14.40Kg/m²

Note: Consumption based on smooth, even, non-absorbent substrate.

Tool cleaning

Clean tools with soapy water. Do not use Triflex Cleaner.

Storage / shelf life

Store unopened in a cool, dry, well ventilated place above freezing, out of direct sunlight and in the original container.

Health and safety

Refer to Safety Data Sheets.

Disposal information

Refer to Safety Data Sheets for recommended EWC waste codes.

Notes

The advice we provide on the application of our products is based on extensive development work and many years of experience, and is given to the best of our knowledge. The wide variety of requirements for a building under the most diverse conditions mean that it is necessary for the contractor to test the product for suitability in each case. Triflex reserve the right to make alterations in keeping with technical developments or improvements.

Non-Triflex products must not be used with Triflex systems.

Only the most recent version of this data sheet is valid.