
## Triflex StairCoat Reinforced (TSS-R) Chips Design

## Fully reinforced system for stairs above occupied spaces

External stairs and stairwells are vulnerable to water, mechanical and chemical damage as they are not only open to the elements but are also susceptible to added downforce pressure from foot traffic, particularly at nosings. It is essential that these areas when over occupied spaces are reliably waterproofed and surfaced with a robust system to protect the integrity of the structure and contents beneath, and to provide a safe and secure environment for users. Featuring a combination of reliable waterproofing, durable surfacing on the treads and proprietary or resin based edge nosings, Triflex StairCoat offers the perfect long term protective solution. The system is ultra fast curing and cold liquid applied, allowing installation to be completed quickly, without the use of hot works, and with minimal impact on users. Triflex Chips Design is one of two unique surface finishes available for Triflex StairCoat, featuring a low maintenance, durable coloured finish and decorative anti-slip chips. With a range of over 50 standard colours, there are countless possibilities available, enabling you to create a tailored solution for your project.



## System highlights

## Dynamic crack bridging, fully reinforced, cold applied system

Triflex lead from the front. Featuring unique resins with enhanced elastomeric properties and high tensile strength fleece reinforcement, we deliver a totally waterproof solution that can accommodate movement and cracking within a structure. There is no risk from hot works during installation as all our materials are applied in a totally cold liquid form, curing to create a solution that lasts.

## Fast curing with rapid installation

Rapid curing and easy to install, Triflex allows buildings to remain occupied during installation, limiting access restrictions and unnecessary disruptions to everyday life. Installation can be carried out all year round and the system still cures quickly at temperatures down to 0°C.

#### Asphalt overlay

Many stairs and stairwells have historically been waterproofed using asphalt which over time will fail. With more than 30 years' experience, Triflex StairCoat is the ideal solution for directly overlaying failing asphalt. In fact, whatever the substrate, we can provide a quick, easy and reliable overlay solution.

## Safety and environmental

Our solvent and isocyanate free resin technology has been assessed under BREEAM principles and can contribute to A+ ratings. The Chips Design finish provides a moderate slip potential when wet in accordance with HSE guidelines. Chips Design is recommended for maintained areas, those which are trafficked infrequently when wet and not for general public access.

#### Versatile design

Available in a wide range of standard and bespoke colours, Chips Design can be tailored to create your ideal finish - refer to Triflex colour card.

### **Application areas**

- External stairs and stairwells over occupied premises
- High risk areas subject to significant levels of structural movement and cracking

## **Compatible substrates**

- Concrete, concrete repair materials and screeds
- Asphalt and polymer modified asphalt
- Existing membranes
- Stee
- Structural plastics
- Timber

#### Suitable constructions

- Cast in situ concrete
- Permanent formwork with in situ concrete
- · Precast concrete planks with or without structural topping
- Precast double tee units with or without structural topping
- Steel / galvanised steel / structural plastic / timber constructions

## **Approvals**

Fully certified to the highest UK and European standards and classifications, including:




ETAG 005 certified (reinforced waterproofing membrane) 25 year expected working life

- · Fire performance:
  - EN ISO-11925-2
- EN ISO-9239-1
- EN 13501-1

#### **Manufacturer certification**

- ISO 9001 Quality Management
- ISO 14001 Environmental Management
- ISO 50001 Energy Management

## System build-up and consumptions



Layer		Product	Consumption (1)	Aggregate / Broadcast	Overcoat / traffic <sup>(2)</sup>
0	Primers	Triflex Cryl Primer 222 / 276 / 287 / 280 White	0.40Kg/m²	-	45 minutes
2	Reinforced waterproofing (single process)	Triflex ProDetail reinforced with Triflex 110g Reinforcement	Resin: 3.00Kg/m <sup>2</sup> Reinforcement: 1.05m <sup>2</sup> /m <sup>2</sup>	-	1 hour
3	Waterproof surfacing layer (treads only)	Triflex ProFloor	4.00Kg/m <sup>2</sup>	-	1 hour
4	Finish	Triflex Cryl Finish 205	0.50kg/m <sup>2</sup>	Triflex MicroChips: 0.05Kg/m <sup>2</sup>	1 hour

<sup>(1)</sup> Minimum consumption assuming a smooth, even, non-absorbent substrate.

## Primary test data

#### Anti-skid

Tests carried out wet on new indicative samples in accordance with UKSRG Guidelines (2016). Based on HSE and UKSRG guidance a surface with a PTV of 36+ is classified as having a low slip potential.

- PTV approx. 39 (Four S rubber / Slider 96)
- PTV approx. 35 (TRRL rubber / Slider 55)

#### **Colours and finishes**

Available in a wide range of colours - refer to Triflex colour card.

## **Next steps**

To ensure a thorough understanding of the construction, the substrate and to determine the most appropriate specification, Triflex carries out free of charge surveys, testing, investigations and analysis prior to preparing a bespoke project specification proposal. To arrange a meeting or site visit please contact Triflex Customer Services.


The advice we provide on the application of our products is based on extensive development work as well as many years of experience and is given to the best of our knowledge. However, the wide variety of requirements for a building under the most diverse conditions means that it is necessary for the Contractor to test the product for suitability in any given case. Triflex reserve the right to make alterations in keeping with technical developments or improvements.

 $<sup>^{(2)}</sup>$  The times stated are based on  $+20^{\circ}$ C – the times will not be significantly extended at low temperatures.

# Triflex StairCoat Reinforced (TSS-R) Chips Design

Notes: There may be slight variations in shade between actual colours and those shown below. RAL colours are approximate.

## Optional finish colours: Triflex colours



5017 Traffic blue

4006 Traffic purple

3020 Traffic red

9005 Jet black

9010 Pure white

2009 Traffic orange

1023 Traffic yellow

6024 Traffic green